

# KLB-SYSTEM ACRYL

## AC 353

Elastic grouting resin on the basis of PMMA for joints that can be driven over

### Packaging units



| Article no. | Packaging | Inhalt   | Units/pallet |
|-------------|-----------|----------|--------------|
| AK0030-47   | Bucket    | 10.00 kg | 30           |
| AK0030-30   | Hobbock   | 25.00 kg | 12           |

### Product characteristics

|                             |  |
|-----------------------------|--|
| Processing time             | 20 °C / 68 °F : 8 - 13 min.  |
| Processing temperature      | Minimum 5 °C / 41 °F (room and floor temperature; at temperatures below this, it is necessary to add accelerator AC-Beschleuniger) |
| Curing time (accessibility) | 20 °C / 68 °F : approx. 60 - 120 minutes (until it is grindable)   |
| Dosage of hardener          | 5 °C / 41 °F: 3.0 - 4.0 %<br>12 °C / 53.6 °F : 2.0 - 3.0 %<br>20 °C / 68 °F : 1.5 - 2.0 %<br>30 °C / 86 °F : 1.0 - 1.5 %           |
| Curing                      | 60 - 120 minutes until accessibility at 20 °C / 68 °F  |
| Consumption                 | (resin with 50% KLB-Mischsand 2/1) approx. 1.65 kg/l<br>(resin with 75% KLB-Mischsand 2/1) approx. 1.8 kg/l                        |
| Colours                     | Grey   |
| Shelf life                  | 6 months (originally sealed)   |

### Product description

**KLB-SYSTEM ACRYL AC 353** is an elastic PMMA grouting compound which is used for producing accessible floor joints. The fast-curing grouting resin requires only short installation times and can thus be used or driven over after just a few hours. The coating can additionally be filled with mixed sand **KLB-Mischsand 2/1** to control the hardness and load-bearing capacity. The application is carried out in block casting in thick layers of up to 40 mm. Due to the fast hardening, the joint can be ground even with the floor after only 1 to 2 hours.

**KLB-SYSTEM ACRYL AC 353** is suitable for grouting building components, connection, industrial and movement joints in layer thicknesses of 10 - 30 mm in one grouting. The elastic deformability allows to absorb the movement of structural components, such as two concrete slabs lying next to each other. **KLB-SYSTEM ACRYL AC 353** is particularly convincing for block joints with little movement and high stress. In contrast to this, **KLB-SYSTEM ACRYL AC 356** has a higher elasticity and should therefore rather be used for joints susceptible to higher deformation.

Due to its deformability, the movement of structural components can be absorbed, while the building joints can still be driven or rolled over. In the case of floor conveyor use, the joints between the building components can be accessed with low noise, which means that the driving speed can be kept high. Shocks and impacts of conventionally installed joint profiles are avoided even with intensive vehicle traffic.

**KLB-SYSTEM ACRYL AC 353** suits application in storage, commercial or industrial facilities as well as for accessible joints on parking decks, underground parking, and much more.

**KLB-SYSTEM ACRYL AC 353** has a medium viscosity and is adjusted with a very pourable consistency; the processing time is short, as with all PMMA resins. The joint can already be ground down to the level of the floor after 1 to 2 hours using a suitable grinding machine. The resin hardens in layer thicknesses of 10 to 30 mm with little shrinkage. Higher thicknesses must be laid in several layers. Depending on the area of application, joint width, mechanical requirements and therefore, desired elasticity, the product can be individually adjusted by filling it with mixed sand **KLB-Mischsand 2/1**. To improve the visual impression of the joints and to increase cleanability, a sealing layer with **KLB-SYSTEM POLYURETHAN PU 9018 Flex Color** can be applied.

**KLB-SYSTEM ACRYL AC 353** is sufficiently hard/elastic within 2 - 3 hours, thus can be walked or rolled over with light weight. Full hardening is achieved after 12-18 hours. If possible, traffic with high frequency and load should only take place after this time.

The joint has good chemical resistance to water, aqueous solutions, diluted acids, glycol and petrol under normal use. Conditional resistance to solvents.

---

#### Area of application

- Hard-elastic grouting of building joints between concrete slabs or as alternative to profiles.
- Block grouting of concrete slabs in commercial or industrial halls that can be driven over by floor conveyors with low vibration and low noise.
- For building, connection, industrial and movement joints in driving or parking areas, also with intensive traffic.
- Suitable for joints with low movement and high stress.

---

#### Product features

- rapid-setting
- quickly accessible
- deformable
- low-shrink
- resistant to water and chemicals
- impervious to fluids
- resistant to weather

---

#### Technical data

|                     |  |                   |                                   |
|---------------------|--|-------------------|-----------------------------------|
| Viscosity           | 800 - 1000   | mPas              | DIN 53018                         |
| Density             | Approx. 1.35 (unfilled), approx. 1.65 (with 50% KLB-Mischsand 2/1), approx. 1.8 (with 75% KLB-Mischsand 2/1) | kg/l              | DIN EN ISO 2811-2 (20 °C / 68 °F) |
| Tensile strength    | approx. 4.7 (with 50% KLB-Mischsand 2/1), approx. 4.5 (with 75% KLB-Mischsand 2/1)                           | N/mm <sup>2</sup> | DIN 53504                         |
| Elongation at break | Approx. 90 (with 50% KLB-Mischsand 2/1), approx. 30 (with 75% KLB-Mischsand 2/1)                             | %                 | DIN EN ISO 527-2                  |
| Shore-hardness A    | Ca. 96 (mit 50 % Mischsand 2/1)  | -                 | DIN 53505 (after 7 days)          |
| Shore-hardness D    | Ca. 45 (mit 50 % Mischsand 2/1)  | -                 | DIN 53505 (after 7 days)          |

The values established in tests are average values. Deviations from the product specification may occur.

### Build-up of coats

Prepare the joints between the concrete slabs mechanically. Existing joints must be dismantled. If necessary, the joint profile is to be chiselled out and reprofiled using a mortar out of **AC 353** and mixed sand **Mischsand 1**. Here, the dimensions must be created in a way that there is sufficient deformation distance between the building components in accordance with their expected movements, so that enough adhesion is provided to the two joint flanks. An elastic separating profile is to be inserted into the substrate. The exposed joint deformation section must be sufficiently dimensioned so that the expansions/deformations can be absorbed.

#### Grouting of accessible joints

- Prime the joint flanks with **AC 20**, consumption approx. 0.35 - 0.45 kg/m<sup>2</sup>.
- Optional: openly sanding the fresh surface with quartz sand 0.7/1.2 mm, consumption approx. 0.5 - 1.0 kg/m<sup>2</sup>.
- If necessary, reprofile break-outs with a mortar consisting of **AC 353** and mixed sand **Mischsand 1** in a mixing ration of 1 : 4 parts by weight. It is possible to lay the mortar wet-in-wet into the primer.
- After the mortar has hardened, the closed joint is opened again by a separating cut, and a closed-cell PE round cord of suitable width is inserted to prevent three-flank adhesion.
- After curing, the elastic grouting mortar filled with 50 - 75% of mixed sand **Mischsand 2/1** can be poured in (depending on driving load and joint movement), so that a slight excess of the material remains (for 1 - 2 mm).
- **Important note:** we do not recommend higher filling than 75%, as this reduces the mechanical properties of the block joint.
- Grind the filled joint flat with the surface of the concrete slab/coating after 1 - 2 hours using a concrete grinder with diamond or PCD cup (depending on the desired grinding effect).
- Apply the optional sealing layer with **PU 9018 Flex Color**, consumption approx. 0.40 - 0.55 kg/m<sup>2</sup>.

---

### Substrate

The component/substrate to be grouted must be even, dry, free of dust, sufficiently resistant to tension and compression as well as be free from weakly-bonded components or surfaces. Materials impairing adhesion such as grease, oil and paint residues should be removed with suitable measures. Substrates suitable for coating are concrete C20/25, cement screed CT-C35-F5 (ZE30) as well as other sufficiently solid substrates. The substrate has to have adequately high strength for the intended occupational use and be dimensioned. The substrates to be coated should be prepared mechanically, preferably by shot blasting. The surface strength must then be at least 1.5 N/mm<sup>2</sup>. For concrete, moisture content must not exceed 4.0 CM-%, remaining residual humidity. The possibility of moisture ingress from the rear must be permanently excluded. Observe the information issued by the trade associations, e.g. the most recent versions of BEB worksheets KH-0/U and KH-0/S.

**The surfaces to be coated must be primed with AC 20.**

---

### Mixing

PMMA resins and hardener powder will be delivered in individual packaging units. Since the curing reaction depends on the prevailing processing temperature, the hardener powder is dosed according to the respective section on hardener dosage.

KLB PMMA resin has to be stirred or agitated to a homogeneous resin mixture before processing. Due to the rapid curing of the material, only partial quantities that can be processed within the pot life should be mixed. The recommended hardener quantities must be observed in any case, as curing problems may occur if too little, and colour changes if too much is added. Empty all of the hardener into the resin component **AC 353** and mix carefully with a slow speed mixer (200 - 400 r/pm) for at least 30 - 60 seconds until the hardener powder is completely dissolved.

For joint grouting, it is recommended to add the hardener powder after the mixed sand. For mortar, it is recommended to add the hardener powder before the mixed sand. Then apply the grouting immediately.

Addition of filling sand for joint grouting

**10 kg AC 353**

**5 - 7.5 kg of mixed sand KLB-Mischsand 2/1**

**Important note:** when industrial trucks are supposed to drive on the floor, it is mandatory to use 7.5 kg of sand (75%).

Producing mortars

**10 kg AC 353**

**40 kg of mixed sand KLB-Mischsand 1**

The amount of mixed sand depends on the necessary consistency and stability. Then process immediately.

---

**Processing**

The joints are cut/chiselled out according to the desired joint profile and freed from loose material. If necessary, clean the joint edges with thinner, e.g. **VR 119**. Then insert a closed-cell PE round cord of suitable joint width to prevent three-flank adhesion. Prime the joint edges with **AC 20** and, if needed, scatter openly with quartz sand 0.7/1.2 mm.

In case of mortared joints, too deep joint cross-sections or uneven substrates, reprofile the joint with a mortar made of **AC 353** and mixed sand **Mischsand 1**. To do so, apply the mortar to the pre-primed joint within a few minutes using a smoothing trowel or another suitable smoothing tool. After 30 - 60 minutes, make a separating cut and insert sealing tape. The mortar can be recoated with **AC 353** without further priming.

The pre-primed joint is then filled with the mixture of **AC 353** and mixed sand **Mischsand 2/1**. Pour the fresh mixture into the joint and spread the material evenly. Fill with excess. For increased layer thicknesses (> 30 mm), a second grouting may be necessary.

After hardening (approx. 1 - 2 hours), the excess material can be removed, e.g. with a concrete grinder incl. diamond cup. A finish grinding might be required using an eccentric grinder. When doing so, grind in a way that the joint is even with the floor surfaces on both sides. After sanding, a sealing layer with **PU 9018 Flex Color** can be applied, when needed.

Floor and air temperature must not fall below 5 °C / 41 °F. If a dew-point situation arises, adhesion may be disrupted. If working conditions are not complied with, the technical properties of the end product may deviate from those specified.

**Note:** PMMA resins are highly flammable and subject to the Ordinance on Hazardous Substances. Observe the instructions in the safety data sheet and on the container!

---

**Cleaning**

To remove fresh contamination and to clean tools, use thinner **VR 119** immediately.

---

#### Storage

Store in dry and at frost-free conditions. Ideal storage temperature is between 10 - 20 °C / 50 - 68 °F. Bring to a suitable processing temperature before application. Tightly re-seal opened packages and use up the content as soon as possible.

#### Special remarks

The product is regulated by the German Ordinance on Hazardous Substances (GefStoffV), the German Ordinance on Industrial Safety and Health (BetrSichV), and transport regulations for hazardous goods. The necessary information is contained in the DIN Safety Data Sheet. Observe all identification information on the container label!

GISCODE: RMA 10

**Indication of VOC-content:**

(EG-Regulation 2004/42) Maximum Permissible Value 500 g/l (2010,II,j/lb): Ready-for-use product contains < 500 g/l VOC.



Please consider the latest version of this product information on our website.

All stated information is based on our experience and technical preparation. We guarantee the correct and proper quality of our products. We do not assume any responsibility for the work not carried out by us, since we have no influence on the processing or processing conditions. We recommend on-site trials to be conducted in individual cases. With the publication of this new KLB product information, all prior information loses validity. The latest version is available electronically on our website [www.klb-koetztal.com](http://www.klb-koetztal.com). In addition, our "General Terms and Conditions" apply.