

KLB-SYSTEM Stellmittel 5 FT

Thixotropic and suspending agent for reactive resins

Packaging units

Article no.	Packaging	Content (kg)	Units/pallet
ZS6954-90	Hobbock	1.50 kg	12
ZS6954-50	Bag	10.00 kg	18

Product description

Suspending agent based on polypropylene fibres for thickening reactive resins when applied to vertical surfaces and slopes as well as for filling pores.

KLB-SYSTEM STELLMITTEL 5 FT can be processed easily and without introducing dust.

- Thickening of primers, e.g. **KLB-SYSTEM EPOXID EP 50** when used as a primer on walls, as scratch coat or for closing joints.
- Thickening of coatings, e.g. **KLB-SYSTEM EPOXID EP 200 VF** for the production of concave skirting.
- Thickening of mortar resins, e.g. **KLB-SYSTEM EPOXID EP 150** with an addition for levelling ramps, holes, indentations, etc.
- Thickening of coatings if slopes must be worked on and moved.
- Versatile thickening agent, multi-purpose and economical.

Processing

Mix resin and hardener based on the processing instructions. Then add suspending agent **KLB-SYSTEM STELLMITTEL 5 FT**, e.g. by means of volumetric dosing (measuring cup or similar), completely stir and refill, if necessary. For example, add 120 - 150 g (= approx. 1.5 l volume dosed) for pebble coatings.

Storage

Can be stored indefinitely long when being in a dry place.

Please consider the latest version of this product information on our website.

All stated information is based on our experience and technical preparation. We guarantee the correct and proper quality of our products. We do not assume any responsibility for the work not carried out by us, since we have no influence on the processing or processing conditions. We recommend on-site trials to be conducted in individual cases. With the publication of this new KLB product information, all prior information loses validity. The latest version is available electronically on our website www.klb-koetzal.com. In addition, our "General Terms and Conditions" apply.