



KLB-SYSTEM EPOXID EP 202 Clean EL+

Low-emission, electrically conductive, coloured and hygienic 2-component epoxy resin coating for producing jointless floors with increased hygiene requirements in EX areas and cleanrooms

Packaging units



| Article no. | Packaging | Content (kg) | Units/pallet |
|-------------|---------------|--------------|--------------|
| AK1423-50 | Bucket combo | 12.00 kg | 30 |
| AK1423-30 | Hobbock combo | 30.00 kg | 12 |

Product characteristics

| | |
|------------------------------|--|
| Mixing ratio parts by weight | A : B = 5 : 1 |
| Mixing ratio parts by volume | A : B = 100 : 35 |
| Processing time | 10 °C / 50 °F : 50 min. 20 °C / 68 °F : 30 min. 30 °C / 86 °F : 20 min. |
| Processing temperature | Minimum 10 °C / 50 °F (room and floor temperature) |
| Curing time (accessibility) | 10 °C / 50 °F : 24 - 36 hrs. 20 °C / 68 °F : 14 - 18 hrs. 30 °C / 86 °F : 10 - 14 hrs. |
| Curing | 2 - 3 days until mechanical load at 20 °C / 68 °F 7 days until chemical load at 20 °C / 68 °F |
| Further coatings | After 14 - 18 hours, but after 48 hours at the latest at 20 °C / 68 °F |
| Consumption | 1.9 - 2.4 kg/m ² |
| Layer thickness | Approx. 1.3 - 1.5 mm |
| Colours | KLB standard colours – see chart. Other colours upon request! |
| Shelf life | 6 months (originally sealed) – Protect from frost! |

Product description

KLB-SYSTEM EPOXID EP 202 Clean EL+ is a low-emission, electrically conductive self-levelling coating based on a 2-component epoxy resin. **KLB-SYSTEM EPOXID EP 202 Clean EL+** belongs to the new generation of environmentally friendly and low-emission epoxy resin coatings, which are formulated without the use of solvents and volatile components.

KLB-SYSTEM EPOXID EP 202 Clean EL + is certified according to the “Indoor Air Comfort Gold” and meets the requirements for a sustainable building certification according to DGNB, LEED or BREEAM. The “Indoor Air Comfort” product certification sets the highest requirements for the emission of volatile organic compounds and meets not only the German requirements of AgBB or ABG, but also the emissions regulations of many other European countries. The conductive coatings can be used in recreation and clean rooms with particular requirements on emissions.

KLB-SYSTEM EPOXID EP 202 Clean EL+ is a 2-component epoxy resin coating which is designed to offer preventive protection against bacterial contamination. This assists the production of permanently hygienic surfaces, even between the necessary cleaning and disinfection cycles.

Note: the information on processing as well as the technical data of **KLB-SYSTEM EPOXID EP 202 Clean EL+** do not deviate from the standard product.

Alternatively, **KLB-SYSTEM EPOXID EP 202 EL+** is a low-emission, electrically conductive self-levelling coating which is not additionally equipped with antibacterial properties.

The coating can be processed in the same way as existing conductive coatings. The self-levelling and smoothing capabilities are very good. Floating and streaking due to conductive components are minimized.

The cured coating is hard, wear-resistant, and suitable to be used in significant industries and commercial areas, where an electrically conductive floor is required.

KLB-SYSTEM EPOXID EP 202 Clean EL+ can therefore be used in pharmaceutical, as well as in the biotechnology and biochemistry industry. In addition to easy cleanability, a good disinfection capability is also required there. The coating is also resistant to hydrogen peroxide fumigation, used for biological decontamination of surfaces.

KLB-SYSTEM EPOXID EP 202 Clean EL+ has a good resistance to many chemicals, like water, salts, saline solutions, alkalis and bases, grease, oil as well as diluted mineral acids like salt and sulfuric acid. A conditional resistance is given for solvents, gasoline, etc; a moderate resistance exists for concentrated mineral acids, for organic acids and chlorinated hydrocarbons. For chemical resistance requirements, please ask for a separate consultation.

Note: slight colour alterations may be possible due to technical reasons

Area of application

- Low-emission and electrically conductive coating for recreation rooms according to the principles of the AgBB-scheme.
- For areas with special requirements to the explosion protection, to prevent electrostatic discharge.
- In the pharmaceutical industry, biotechnology and biochemistry for surfaces decontaminated with hydrogen peroxide.
- For electrically conductive, commercially used areas with medium mechanical load, e.g. production or storage areas in many economic sectors.

Product features

- tested, low-emission quality
 - Total Solid according to GISCODE (Test method "Deutsche Bauchemie")
 - good processing properties
 - electrically conductive
 - hygienic
 - available in light colours
 - even surface
 - resistant to abrasion and wear
 - good resistance to water and chemicals
-

Technical data

| | | | |
|---------------------------|---|-------------------|--------------------------------------|
| Viscosity - Component A+B | 1500 - 2000 | mPas | DIN EN ISO 3219 (23 °C / 73.4 °F) |
| Density - Component A+B | 1.60 | kg/l | DIN EN ISO 2811-2 (20 °C / 68 °F) |
| Bending tensile strength | 60 | N/mm ² | DIN EN 196/1 |
| Compressive strength | 78 | N/mm ² | DIN EN 196/1 |
| Shore-hardness D | 81 | - | DIN 53505 (after 7 days) |
| Abrasion (Taber Abraser) | 47 | mg | ASTM D4060 (CS10/1000) |
| Electrical resistance | (in combination with EP 799 Ableitgrund) Approx. 10 ⁶ | Ohm | DIN IEC 61340-5-1/2 DIN EN 61340-4-1 |

The values established in tests are average values. Deviations from the product specification may occur.

Included in systems

- System F8 - KLB CONDUCTIVE CLEAN EP EX

Please visit our website to get more information about our KLB systems: www.klb-koetzal.com

Tests

The following external test certificates are available:

- Classification of the fire behavior according to DIN EN 13501-01:2010-01: B_{fl}-s1.
- Certified as low-emission according to Eurofins "Indoor Air Comfort Gold". Compliant with AgBB and suitable for recreation rooms.
- Resistant to decontamination with hydrogen peroxide vapours
- Bacteriostatic activities according to ISO 22196:2011-08 and JIS 2801:2000.
- Suitable for use in foodstuffs according to § 31 para. 1, German Food and Feed Code (german law LFGB).
- Product is compliant with DIN EN 13813: 2003-01.

Note:

Please ask for the tested system build-up!

Build-up of coats

- Test and prepare the substrate, preferably by shot-blasting.
- Prime with **EP 57**, consumption approx. 0.3 - 0.4 kg/m². Apply with a rubber squeegee or a roller.
- Apply a scratch coat for an even surface, e.g. with **EP 57** and mixed sand **KLB-Mischsand 2/1**. Mixing ratio 1 : 0.5 - 0.8 parts by weight, consumption approx. 0.6 - 1.0 kg/m².
- Glue in copper bands for discharge in an imagined grid-pattern in place into the room - every 6 - 8 m, up to 1 - 2 m. Earth connection by an electrician based on VDE regulations.
- Apply a cross-conductible coat with **EP 799 Ableitgrund**, consumption approx. 0.100 - 0.140 kg/m².
- Apply the conductive coat **EP 202 Clean EL+** with a toothed trowel, e.g. **Toothed blade RS 4** or Pajarito 48, consumption approx. 1.9 - 2.4 kg/m².

Substrate

The substrate to be coated must be even, dry, free of dust, sufficiently resistant to tension and compression as well as be free from weakly-bonded components or surfaces. Materials impairing adhesion such as grease, oil and paint residues should be removed with suitable measures. Observe the information issued by the trade associations, e.g. the most recent versions of BEB worksheets KH-0/U and KH-0/S as well as the notes provided in the product information for the recommended base coats, like **EP 58**, **EP 57**, or **EP 53 Spezialgrund AgBB**. The surface strength must then be at least 1,5 N/mm². For concrete, moisture content

must not exceed 4.5 CM-%, remaining residual humidity. The possibility of moisture ingress from the rear must be permanently excluded. Base coats may not be left open for more than 48 hours or must be scattered with quartz sand. The substrates to be coated should be prepared mechanically, preferably by shot-blasting. The prepared area must be saturated, pore-free and primed carefully. It is often difficult to judge the necessary pore-free condition of substrates. It is therefore recommended that a scratch coat be applied to smooth the surface. If the substrate has not been primed to be pore-free, bubbles and pores can develop in the coating due to air rising from the substrate. Old substrates must be cleaned before any mechanical preparation. If old synthetic resin surfaces are being sealed, it is necessary to check that sufficient adhesion is achieved. If in doubt, we recommend processing a sample area. Reconstruction beyond the regular requirements demands further substrate testing, e.g. by conducting a tensile bonding test.

Conductive coatings must be applied in the required layer thickness, it is thus mandatory to prepare the substrate thoroughly.

Mixing

Combo-packaging will be supplied in the correctly measured mixing ratio. The package of Component A has sufficient volume to contain the entire packaging unit. Empty all of the hardener compound B into the resin. Blend with a slow speed mixer (200 - 400 r/pm) for at least 2 - 3 minutes until a homogeneous, streak-free compound forms. To prevent mixing errors, empty ("repot") the resin/hardener mixture into a clean container and mix it once again briefly.

Processing

Process the material immediately after mixing with a squeegee or toothed trowel (e.g. **Toothed blade RS4** or Pajarito 48) by pulling out an even layer on the prepared substrate. The product is adjusted for optimum deaeration, however, for conductive coatings, rolling with a spiked roller is mandatory to optimise the conductivity. This should be carried out time-delayed after approx. 10 - 15 minutes. In order to work seamlessly, always work "fresh-in-fresh" and define work areas before starting.

Check consumption during application, as it may be reduced by wear of the teeth on the toothed blade. If the blade is worn, it must be replaced by the applicator in order to maintain the recommended consumption quantities.

Floor and air temperature must not fall below 10 °C / 50 °F and humidity should not exceed 75 %. The difference in floor and room temperature must remain less than 3 °C / 3 K / 5.4 °F so as not to impede the curing process. If a dew-point situation arises, regular curing will not be possible with hardening problems (carbamate formation) and spotting to occur. Exposure to water should be avoided during the first 7 days. The specified hardening times apply for 20 °C / 68 °F; temperatures below this require longer processing and curing times, while higher temperatures require shorter times. If working conditions are not complied with, the technical properties of the end product may deviate from those specified (surface and load capacity).

Cleaning

To remove fresh contamination and to clean tools, use **VR 24** or **VR 33** immediately. Hardened material can only be removed mechanically.

Separate cleaning and care recommendations are available for cleaning floors produced with KLB coatings and sealers.

Storage

Store in dry and if possible, at frost-free conditions. Ideal storage temperature is between 10 - 20 °C / 50 - 68 °F. Bring to a suitable processing temperature before

application. Tightly re-seal opened packages and use up the content as soon as possible.

Special remarks

The product is regulated by the German Ordinance on Hazardous Substances (GefStoffV), the German Ordinance on Industrial Safety and Health (BetrSichV), and transport regulations for hazardous goods. The necessary information is contained in the DIN Safety Data Sheet. Observe all identification information on the container label! EP 202 Clean EL+: please use biocide products carefully. Before using our products, always read the label and product information.

GISCODE: RE30

Indication of VOC-content:

(EG-Regulation 2004/42) Maximum Permissible Value 500 g/l (2010,II,j/lb): Ready-for-use product contains < 500 g/l VOC.

CE marking

| | |
|--|---------------------|
|  | |
| KLB Kötztal Lacke + Beschichtungen GmbH Günztalstraße 25 FRG-89335 Ichenhausen | |
| 17 | |
| EP202EL+/EP202CleanEL+-V1-012017 | |
| DIN EN 13813:2003-01 | |
| Synthetic resin screed mortar DIN EN 13813: SR-B1.5-AR0.5-IR10 | |
| Fire behaviour | B _{fl} -s1 |
| Emission of corrosive substances | SR |
| Wear resistance BCA | AR 0.5 |
| Adhesive tensile strength | B 1.5 |
| Impact resistance | IR 10 |

VOC content

The product complies with the high requirements to low VOC contents, as required for sustainable construction. Therefore, these values are well below the limits set by the European Union directive 2004/42/EG (Decopaint Directive).

| | Limit value | Actual content | |
|--|-------------|----------------|-----|
| Decopaint Directive 2004/42/EG - Component A | < 500 | 7,4 | g/l |
| Decopaint Directive 2004/42/EG - Component B | < 500 | 19,2 | g/l |
| DGNB - Components A + B | < 3 | 0,63 | % |
| Klima:aktiv - Components A + B | < 3 | 0,63 | % |
| LEED - Components A + B | < 100 | 10,7 | g/l |
| Minergie ECO ® - Components A + B | <1 (< 2) | 0,63 | % |

(According to the Decopaint directive, single components are used for calculation. In the sustainable building rating systems, the mixture of both components in the correct mixing ratio is the determining factor.)



Please consider the latest version of this product information on our website.

All stated information is based on our experience and technical preparation. We guarantee the correct and proper quality of our products. We do not assume any responsibility for the work not carried out by us, since we have no influence on the processing or processing conditions. We recommend on-site trials to be conducted in individual cases. With the publication of this new KLB product information, all prior information loses validity. The latest version is available electronically on our website www.klb-koetzal.com. In addition, our "General Terms and Conditions" apply.