

KLB-STRUKTURGRANULAT

Strukturgranulat RQX 10

For creating slip-resistant coatings for smooth, self-levelling surfaces

Packaging units

Article no.	Packaging	Content (kg)
ZA1281-60	Bucket	6.00 kg

Product characteristics

Appearance	White powder
Application quantity	approx. 0.02 - 0.04
Density	0.9 kg/l

Product description

High-quality structuring agent to be blown into self-levelling coatings with the help of a flocking gun (Chiron device) for increasing the slip resistance to grade R10 in accordance with BGR 181. Under certain conditions, it is also suitable for a selection of conductive coatings, please seek advice if necessary. Observe the respective test certificates.

- Blowing the structuring agent into self-levelling coatings: **KLB-SYSTEM EPOXID EP 99, EP 100 VS, 200 VF, EP 202, EP 213/EP213 Rapid, EP 216 Universal, EP 220, EP 285CR, EP 282 WHG** or **KLB-SYSTEM POLYURETHAN PU 410, PU 420, PU 421, PU 425**. Consumption approx. 0.030 - 0.040 kg/m².

Processing

Mix the resin and hardener of the self-levelling coating used according to the product information and apply the mixture to the substrate. Depending on the product information, spike for 10 - 30 minutes. Then spray **KLB-SYSTEM STRUKTURGRANULAT RQX 10** evenly onto the fresh surface using Chiron equipment in the recommended application quantity. Observe the application quantities depending on the product, and consult the test certificate if necessary. In case of conductive coatings, excessive consumption may reduce the conductive properties. It is mandatory to adhere to the consumption quantities for obtaining the required degree of slip-resistance.



Please consider the latest version of this product information on our website.

All stated information is based on our experience and technical preparation. We guarantee the correct and proper quality of our products. We do not assume any responsibility for the work not carried out by us, since we have no influence on the processing or processing conditions. We recommend on-site trials to be conducted in individual cases. With the publication of this new KLB product information, all prior information loses validity. The latest version is available electronically on our website www.klb-koetztal.com. In addition, our "General Terms and Conditions" apply.