

KLB-SYSTEM STELLMITTEL

Stellmittel 3 Super

Thixotropic and thickening agent for reactive resins

Appearance	White powder
Powder density	50 g/l
Quantity	Depending on application 2 - 5 percentage weight on resin

Application and Properties

Suspending agent based on precipitate silica, for thickening reactive resins when applied to vertical surfaces and slopes as well as for filling pores.

Note: No application with **KLB-SYSTEM POLYURETHAN PU 410!**

- Thickening of coatings, e.g., **KLB-SYSTEM EPOXID EP 200 VF** for the production of concave skirting.
- Thickening of mortar resin, e.g., **KLB-SYSTEM EPOXID EP 150** with the addition for levelling ramps, levelling holes, depressions, etc.
- Thickening of coatings if bevels must be worked on and moved.
- Versatile thickening agent, multi-purpose and economical.

Processing

Mix resin and hardener as per the processing instructions. Then add **KLB-SYSTEM Stellmittel 3 Super**, e.g. by means of volumetric dosing (measuring cup or similar) completely stir; refill, if necessary. For example, add 120 - 150 g (= approx. 3 l volume dosed) for pebble coating.

Storage

Can be stored indefinitely in dry conditions!

Stellmittel 5 FT

Thixotropic and thickening agent for reactive resins

Appearance	White, fibrous powder
Powder density	80 g/l
Quantity	Depending on application 2 - 5 percentage weight on resin

Application and Properties

Suspending agent based on polypropylene fibres, for thickening reactive resins when applied to vertical surfaces and slopes as well as for filling pores. **Stellmittel 5 FT** can be handled easily and incorporated without introducing dust.

- Thickening of primers, e.g., **KLB-SYSTEM EPOXID EP 50** when used as a primer on walls, scratch coat or for sealing joints.
- Thickening of coatings, e.g., **KLB-SYSTEM EPOXID EP 200 VF** for the production of concave skirting.
- Thickening of mortar resin, e.g., **KLB-SYSTEM EPOXID EP 150** with the addition for levelling ramps, levelling holes, depressions, etc.
- Thickening of coatings if bevels must be worked on and moved.
- Versatile thickening agent, multi-purpose and economical.

Processing

Mix resin and hardener as per the processing instructions. Then add **KLB-SYSTEM Stellmittel 5 FT**, e.g. by means of volumetric dosing (measuring cup or similar) completely stir; refill, if necessary. For example, add 120 - 150 g (= approx. 1.5 l volume dosed) for pebble coating.

Storage

Can be stored indefinitely in dry conditions!